

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 07-097240

(43)Date of publication of application : 11.04.1995

(51)Int. Cl. C03C 27/12
B32B 27/30

(21)Application number : 05-241143

(71)Applicant : SEKISUI CHEM CO LTD

(22)Date of filing : 28.09.1993

(72)Inventor : HATTORI TSUYOSHI

(54) INTERLAYER FOR LAMINATED GLASS**(57)Abstract:**

PURPOSE: To improve the sound insulation and optical strain of the laminated glass by using a laminated film composed of specific two kinds of polyvinyl acetal resin as an interlayer.

CONSTITUTION: A polyvinyl alcohol having 500-3000 of average polymerization degree and 78-92% of saponification degree is reacted with a 4-6C aldehyde to obtain a polyvinyl acetal resin having 40mol% or higher of acetalization degree, and 100 pts.wt. of this resin is kneaded with 35-65 pts.wt. of a plasticizer to obtain a resin film (A) having thickness of ≥ 0.05 mm. Besides, a polyvinyl alcohol having average polymerization degree of 500-3000 and saponification degree of $\geq 96\%$ is reacted with a 3-4C aldehyde to obtain a polyvinyl acetal resin having ≥ 50 mol% of acetalization degree, and 100 pts.wt. of this resin is kneaded with 25-55 pts.wt. of a plasticizer to obtain a resin film (B). It is preferable that the objective interlayer be made up of a sum of two or more layers of the films A and B (esp. B/A/B construction); the interlayer is so constituted as to be 0.3-1.6mm in the overall thickness and also that the thicknesses of A and B are 9-25% and ≥ 0.2 mm of a total respectively.

LEGAL STATUS

[Date of request for examination] 18.04.2000

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number] 3335436

[Date of registration] 02.08.2002

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office